

## FINfloor Durable XL

CLASSIFICATION ACCORDING TO EN 685

Rev: 01/03/2022

### CARACTERISTIQUES

USE LEVEL

DOMESTIC INTENSE, COMMERCIAL INTENSE

### TEST METHOD

EN 685:95 ANNEX A

CLASS



33

EXAMPLES: HALLS,  
DEPARTMENT STORES,  
SCHOOLS, MULTIPURPOSE  
ROOMS, OPEN OFFICE (OPEN  
LAYOUT)

### GENERAL SPECIFICATIONS

#### CARACTERISTIQUES

Thickness of element (t);  
t = 10 mm



$\Delta t_{av}$ , (relative to nominal value) 0,50  
t max - t min 0,50

EN 13329 ANNEX A

Length of the surface layer (l) l = 1780 mm

$\Delta l_{0,5}$

EN 13329 ANNEX A; EN 13329  
ANNEX A

Width of the decorative surface (w)  
w = 246 mm

$\Delta w_{av}$ , (relative to nominal value) 0,10 w max - w min 0,20

EN 13329 ANNEX A

Squareness of the element (q)

Qmax = < 0,10 mm

EN 13329 ANNEX A

Straightness of the surface layer (s)

smax = < 0,30 mm

EN 13329 ANNEX A

Longitudinal flatness (f)

fconcave = < 6 mm fconvex = < 6 mm

EN 13329 ANEXO A

Transversal flatness (f)

fconcave = < 0,28 mm fconvex = < 0,28 mm

EN 13329 ANEXO A

Opening between elements (o)

oaverage = < 0,15 omax = < 0,20

EN 13329 ANNEX B

Height between elements (h)

haverage = < 0,07 hmax = < 0,10

EN 13329 ANNEX B

Dimensional variations after changes in relative humidity  
(l,w)



$\Delta l_{av}$  = < 0,9 dwaverage = < 0,9








EN 13329 ANNEX C

Light fastness










Blue wool scale, part B02, not worse than 6 Grey scale, part A02, higher or equal to 4

EN-ISO 105 / EN 20105

Static indentation		No visible changes i.e. $\leq 0,01$ mm indentation using a straight steel cylinder with 11,30 mm in diameter	EN 433
Surface soundness		$\geq 1,25$ N/mm <sup>2</sup>	EN 13329 ANNEX D
<b>CLASSIFICATION REQUIREMENTS AND LEVEL OF USE</b>			
<b>CARACTERISTIQUES</b>		<b>REQUIREMENT</b>	<b>TEST METHOD</b>
Abrasion resistance		AC 6	EN 13329 ANNEX E
Impact resistance		IC 3	EN 13329 ANNEX F
Staining resistance		5 (gr 1 - 2) 4 (gr. 3)	EN 438
Effect of a furniture leg		No damage shall be visible when tested with foot	EN 424
Effect of a castor chair		No changes in appearance or damage, as defined in EN425. Single-wheel castor, as defined in EN 12529:1998, 5.4.4.2. (Type W).	EN 425
Thickness swelling		$\leq 8,0\%$	EN 13329 ANNEX G

#### ADDITIONAL PROPERTIES

CARACTERISTIQUES	REQUIREMENT	TEST METHOD
Humidity at dispatch from manufactured	The element shall have a moisture content of 4% to 10%. Any single batch must be homogeneous with $H_{max} - H_{min} = < 3\%$	EN 322
Appearance, surface defects	Minor surface defect as defined in EN438 are permitted	EN 438

Edges sealing		Complete edge sealed with oil-wax product for enhance water resistant	INTERNAL
Mechanical locking strenght		fmax long. >=5 KN/m fmax transv. >=5 KN/m f0,2 long. >=3 KN/m f0,2 transv. >=3 KN/m	ISO 24334:2006
Formaldehyde emissions HCHO		0.11 ppm	CARB PHASE 2/EPA TSCA TITLE VI ASTM E 1333-14
PCP Content		Undetectable	EN 14041 / CEN/TR14823
Reaction to fire		Bfl s1	EN 14041 / EN 13501-1 / EN ISO 9239-1 / EN ISO 11925-2
Slip resistance coefficient under dry conditions		Class DS (>=0,3)	EN 14041 / EN 13893
Slip resistance		Rd>35 Class 2 *	EN 12633:2003 CTE DB SUA 1
Electrical behaviour		The measurement of the body voltage at 23°C/25% humidity are ≤ 2kV. Fulfils the criterions for the classification as an Antistatic Floor Covering	EN 14041 / EN 1815
Electrical behaviour / vertical resistance		Antistatic Floor "ASF – Class 2" in accordance with the international standard IEC 61340-4-1:1995	EN 14041 / EN 1815
Thermal Resistance		Without Underlay: 0,06 m2·K/W + FINfloor PE Underlay 0,154 m 2·K/W + Finfloor Silent Underlay 0,127 m 2 ·K/W Suitable for warm-water underfloor heating systems	EN 14041 / EN 12664
Antibacterial efficiency		Reduction of bacterial activity in 24 hours ≥ 99.9% according to tests carried out at the IMSL	ISO 22196
CE Certificate		DoP 08025_1	EN 14041

The above information is subject to modifications for the benefit of further improvements.

\* Only VERA texture

Non dangerous product. Adequate ergonomic techniques and IPEs must be used when handling. Dust generated in cutting, sanding, drawmilling and other processes must be extracted from the working environment with the usual procedures in the wood industry as industrial vacuum systems and IPEs use must be observed according to law.